





# JFETIGER™

*Premium Connection*





## JFETIGER™ Connection Performance Envelope



### Available Size Range

7" to 9<sup>7</sup>/<sub>8</sub>"

### Wall Thickness

Up to 0.700"


- Run-out pin thread and coupling provide 100% pipe body tension
- Standard and special clearance coupling ODs
- Carbon steel and Chrome grades
- Streamlined ID profile design
- Tested with ISO 13679 2002 and DIS 2009 and field-proven



## DESIGN FEATURES

JFETIGER™ has been designed and tested to meet the needs for critical well loads. The design incorporates metal-to-metal seals with a 17° internal torque shoulder to ensure sealing under extreme loads. The negative load flank thread form and coupled design provide 100% tension efficiency for the standard coupling.

Special clearance coupling OD's are available with full pipe body internal and external pressure ratings.



### Design Advantage

- Reduced gap between stabbing flanks on the pipe and coupling thread ➔ Increased resistance to damage from compressive loads
- Negative load flank angle on threads ➔ Increased tensile and bending capacity while maintaining gas tight seal
- 25 degree angle for thread stabbing flank ➔ Quick make up and increased resistance to cross threading
- Different corner radius for load flanks for pipe and coupling threads ➔ Increased resistance to galling

# JFETIGER™ CASING PERFORMANCE

STANDARD CONNECTIONS			PIPE				CONNECTION				80 KSI		
OD	Nominal Weight	Nominal Wall	Nominal Pipe ID	Pipe Area	Drift	Special Drift	Coupling OD	Coupling ID	Make-Up Loss	Coupling Length	Joint Strength	Internal Pressure	Collapse Pressure
in	lb/ft	in	in	in <sup>2</sup>	in	in	in	in	in	in	kips	psi	psi
<b>7</b>	23.00	0.317	6.366	6.655	6.241		7.713	6.300	5.101	11.487	532	6,340	3,830
	26.00	0.362	6.276	7.549	6.151		7.776	6.210	5.101	11.487	604	7,240	5,410
	29.00	0.408	6.184	8.449	6.059		7.815	6.130	5.101	11.487	676	8,160	7,030
	32.00	0.453	6.094	9.317	5.969	6.000	7.829	6.051	5.101	11.487	745	9,060	8,610
	35.00	0.498	6.004	10.172	5.879		7.896	5.990	5.101	11.487	814	9,960	10,190
	38.00	0.540	5.920	10.959	5.795		7.944	5.933	5.101	11.487	877	10,800	11,390
<b>7 5/8</b>	29.70	0.375	6.875	8.541	6.750		8.343	6.839	5.508	12.303	683	6,890	4,790
	33.70	0.430	6.765	9.720	6.640		8.417	6.706	5.508	12.303	778	7,900	6,560
	39.00	0.500	6.625	11.192	6.500		8.500	6.608	5.508	12.303	895	9,180	8,820
	42.80	0.562	6.501	12.470	6.376		8.572	6.521	5.508	12.303	998	10,320	10,820
	45.30	0.595	6.435	13.141	6.310		8.626	6.475	5.508	12.303	1,051	10,920	11,510
	47.10	0.625	6.375	13.744	6.250		8.675	6.434	5.508	12.303	1,100	11,480	12,040
<b>8 5/8</b>	40.00	0.450	7.725	11.557	7.600	7.625	9.562	7.690	5.508	12.303	925	7,300	5,530
	44.00	0.500	7.625	12.763	7.500		9.562	7.609	5.508	12.303	1,021	8,120	6,950
	49.00	0.557	7.511	14.118	7.386		9.670	7.530	5.508	12.303	1,129	9,040	8,570
	52.00	0.595	7.435	15.010	7.310		9.740	7.477	5.508	12.303	1,201	9,660	9,660
	54.00	0.625	7.375	15.708	7.250		9.794	7.436	5.508	12.303	1,257	10,140	10,510
	57.40	0.656	7.313	16.423	7.188		9.850	7.393	5.508	12.303	1,314	10,650	11,240
	58.70	0.687	7.251	17.132	7.126		9.905	7.350	5.508	12.303	1,371	11,150	11,730
	59.20	0.700	7.225	17.428	7.100		9.928	7.332	5.508	12.303	1,394	11,360	11,930
<b>9 5/8</b>	40.00	0.395	8.835	11.454	8.679	8.750	10.485	8.800	5.508	12.303	916	5,750	3,090
	43.50	0.435	8.755	12.559	8.599		10.485	8.732	5.508	12.303	1,005	6,330	3,810
	47.00	0.472	8.681	13.572	8.525		10.520	8.671	5.508	12.303	1,086	6,870	4,760
	53.50	0.545	8.535	15.546	8.379	8.500	10.625	8.550	5.508	12.303	1,244	7,930	6,620
	58.40	0.595	8.435	16.879	8.279	8.375	10.657	8.492	5.508	12.303	1,350	8,650	7,900
	59.40	0.609	8.407	17.250	8.251		10.681	8.472	5.508	12.303	1,380	8,860	8,250
<b>9 7/8</b>	62.80	0.625	8.625	18.162	8.469	8.500	11.063	8.709	5.758	12.803	1,453	8,860	8,260
	65.30	0.650	8.575	18.838	8.419		11.063	8.668	5.758	12.803	1,507	9,220	8,880
	66.40	0.661	8.553	19.134	8.397		11.063	8.650	5.758	12.803	1,531	9,370	9,150
	66.90	0.668	8.539	19.322	8.383		11.063	8.639	5.758	12.803	1,546	9,470	9,330
	67.50	0.678	8.519	19.590	8.363		11.063	8.621	5.758	12.803	1,567	9,610	9,580
	68.00	0.694	8.487	20.017	8.331		11.063	8.595	5.758	12.803	1,601	9,840	9,980
	68.90	0.700	8.475	20.177	8.319		11.063	8.585	5.758	12.803	1,614	9,920	10,120

SPECIAL CLEARANCE CONNECTIONS			PIPE				CONNECTION				80 KSI		
OD	Nominal Weight	Nominal Wall	Nominal Pipe ID	Pipe Area	Drift	Special Drift	Coupling OD	Coupling ID	Make-Up Loss	Coupling Length	Joint Strength	Internal Pressure	Collapse Pressure
in	lb/ft	in	in	in <sup>2</sup>	in	in	in	in	in	in	kips	psi	psi
<b>8 5/8</b>	44.00	0.500	7.625	12.763	7.500		SC90 9.485	7.609	5.508	12.303	919	8,120	6,950
	58.70	0.687	7.251	17.132	7.126		SC90 9.740	7.350	5.508	12.303	1,234	11,150	11,730
	59.20	0.700	7.225	17.428	7.100		SC83 9.625	7.332	5.508	12.303	1,157	11,360	11,930
<b>9 5/8</b>	53.50	0.545	8.535	15.546	8.379	8.500	SC84 10.475	8.550	5.508	12.303	1,045	7,930	6,620

**Note:** All data published in this catalog is accurate at time of publishing and are subject to change. Please consult JFETC.com for current performance and torque data.

	95 KSI				110 KSI				125 KSI			
Compression	Joint Strength	Internal Pressure	Collapse Pressure	Compression	Joint Strength	Internal Pressure	Collapse Pressure	Compression	Joint Strength	Internal Pressure	Collapse Pressure	Compression
kips	kips	psi	psi	kips	kips	psi	psi	kips	kips	psi	psi	kips
506	632	7,530	4,150	601	732	8,720	4,440	695	832	9,910	4,650	790
574	717	8,600	5,890	681	830	9,960	6,230	789	944	11,310	6,450	896
642	803	9,690	7,840	763	929	11,220	8,530	883	1,056	12,750	9,110	1,003
708	885	10,760	9,740	841	1,025	12,460	10,780	974	1,165	14,160	11,710	1,106
773	966	11,830	11,650	918	1,119	13,700	13,030	1,063	1,272	15,560	14,320	1,208
833	1,041	12,830	13,430	989	1,206	14,850	15,130	1,145	1,370	16,880	16,740	1,301
649	811	8,180	5,130	771	940	9,470	5,350	893	1,068	10,760	5,670	1,014
739	923	9,380	7,270	877	1,069	10,860	7,870	1,016	1,215	12,340	8,340	1,154
851	1,063	10,900	10,000	1,010	1,231	12,620	11,080	1,170	1,399	14,340	12,060	1,329
948	1,185	12,250	12,410	1,125	1,372	14,190	13,930	1,303	1,559	16,120	15,350	1,481
999	1,248	12,970	13,670	1,186	1,445	15,020	15,440	1,373	1,643	17,070	17,110	1,560
1,045	1,306	13,630	14,300	1,240	1,512	15,780	16,550	1,436	1,718	17,930	18,700	1,632
878	1,098	8,670	6,020	1,043	1,271	10,040	6,400	1,208	1,445	11,410	6,640	1,372
970	1,212	9,640	7,740	1,152	1,404	11,160	8,420	1,334	1,595	12,680	8,980	1,516
1,073	1,341	10,740	9,700	1,274	1,553	12,430	10,740	1,475	1,765	14,130	11,660	1,677
1,141	1,426	11,470	11,010	1,355	1,651	13,280	12,280	1,569	1,876	15,090	13,440	1,782
1,194	1,492	12,050	12,040	1,418	1,728	13,950	13,490	1,641	1,963	15,850	14,850	1,865
1,248	1,560	12,640	13,110	1,482	1,807	14,640	14,750	1,716	2,053	16,640	16,310	1,950
1,302	1,628	13,240	13,930	1,546	1,885	15,330	16,010	1,790	2,142	17,420	17,760	2,034
1,325	1,656	13,490	14,170	1,573	1,917	15,620	16,410	1,821	2,178	17,750	18,370	2,070
870	1,088	6,820	3,330	1,034	1,260	7,900	3,470	1,197	1,432	8,980	3,530	1,360
954	1,193	7,510	4,130	1,133	1,381	8,700	4,420	1,312	1,570	9,890	4,620	1,491
1,031	1,289	8,150	5,090	1,225	1,493	9,440	5,300	1,418	1,697	10,730	5,630	1,612
1,182	1,477	9,410	7,340	1,403	1,710	10,900	7,950	1,625	1,943	12,390	8,440	1,846
1,283	1,604	10,280	8,880	1,523	1,857	11,900	9,770	1,764	2,110	13,520	10,540	2,004
1,311	1,639	10,520	9,320	1,557	1,897	12,180	10,280	1,803	2,156	13,840	11,130	2,048
1,380	1,725	10,520	9,320	1,639	1,998	12,180	10,290	1,898	2,270	13,840	11,140	2,157
1,432	1,790	10,940	10,070	1,700	2,072	12,670	11,170	1,969	2,355	14,400	12,160	2,237
1,454	1,818	11,130	10,400	1,727	2,105	12,890	11,560	1,999	2,392	14,640	12,610	2,272
1,468	1,836	11,250	10,610	1,744	2,125	13,020	11,810	2,019	2,415	14,800	12,900	2,294
1,489	1,861	11,410	10,910	1,768	2,155	13,220	12,160	2,047	2,449	15,020	13,310	2,326
1,521	1,902	11,680	11,400	1,807	2,202	13,530	12,730	2,092	2,502	15,370	13,970	2,377
1,533	1,917	11,780	11,580	1,821	2,219	13,650	12,940	2,108	2,522	15,510	14,210	2,396

	95 KSI				110 KSI				125 KSI			
Compression	Joint Strength	Internal Pressure	Collapse Pressure	Compression	Joint Strength	Internal Pressure	Collapse Pressure	Compression	Joint Strength	Internal Pressure	Collapse Pressure	Compression
kips	kips	psi	psi	kips	kips	psi	psi	kips	kips	psi	psi	kips
873	1,091	9,640	7,740	1,037	1,264	11,160	8,420	1,200	1,436	12,680	8,980	1,364
1,172	1,465	13,240	13,930	1,392	1,696	15,330	16,010	1,611	1,927	17,420	17,760	1,831
1,099	1,374	13,490	14,170	1,305	1,591	15,620	16,410	1,512	1,808	17,750	18,370	1,718
992	1,241	9,410	7,340	1,179	1,436	10,900	7,950	1,365	1,632	12,390	8,440	1,551

## JFETIGER™ connections within a given OD are interchangeable with the following provisions:

- Pin and Box ID are optimized based on the specified pipe weight. When a lighter weight connection is made up with a heavier weight, a small step may occur depending on the differing connection ID's. Refer to the connection dimensional data to determine the step dimension.
- When making up a lighter weight to a heavier weight, the torque values for the lighter weight should be used.
- When making up connections of differing grades (yield strengths), the torque values of the lower yield strength should be used.
- Connection performance is that of the lighter weight/lower yield strength connection.

*\*Note: For more information pertaining to interchangeability data, please contact JFE-TC.*

## JFETIGER™ Test History

Pipe OD	Lb/Ft	Wall	Material Grade	Test Protocol	Tension (% TLE)	Comp. (% TLE)	Collapse (% API)	Bending (°/100ft)
7.000	32.00	0.453	P110	ISO 13679 2002 CAL IV	100%	95%	100%	20°
7.000	38.00	0.540	Q125	ISO DIS 2009 mod. CAL IV	100%	95%	100%	20°
7.625	33.70	0.430	HP2 13Cr-95	ISO 13679 2002 CAL IV	100%	95%	100%	20°
7.625	39.00	0.500	P110	ISO DIS 2009 mod. CAL IV	100%	95%	100%	20°
7.625	47.10	0.625	Q125	ISO DIS 2009 mod. CAL IV	100%	95%	100%	20°
8.625	59.20	0.700	Q125	ISO DIS 2009 mod. CAL IV	83% (SC)	79%	100%	20°
9.625	53.50	0.545	HP2 13Cr-95	ISO 13679 2002 CAL IV	100%	95%	100%	20°
9.625	53.50	0.545	P110	ISO DIS 2009 mod. CAL IV	100%	95%	100%	20°
9.625	53.50	0.545	Q125	ISO DIS 2009 mod. CAL IV	100%	95%	100%	20°
9.875	68.90	0.700	110SS	ISO 13679 2002 CAL IV	100%	95%	100%	20°
9.875	68.90	0.700	UHP 15Cr-125	ISO DIS 2009 mod. CAL IV	100%	95%	100%	20°

**TLE:** Test Load Envelope



# JFE-TC Global Presence

[www.jfetc.com](http://www.jfetc.com)



## Technical Centers

### JFE-TC HOUSTON

10777 Westheimer, Suite 1010  
Houston, TX 77042  
USA

**TEL +1 713-986-9000**

### JFE-TC SINGAPORE

31 Jurong Port Rd  
05-10 Jurong Logistics Hub  
Singapore 619115

**TEL +65-6264-1801**

## Regional Offices

### JFE-TC UK ABERDEEN

56 Queens Road,  
Aberdeen, AB15 4YE

**TEL +44 1224 209333**  
DIRECT +44 1224 810129  
FAX +44 1224 209501

### JFE-TC DUBAI

P.O. Box 18192, LOB 16 Office No. 404,  
Jebel Ali, Dubai, UAE.

(c/o Marubeni Itochu Steel Inc Jebel Ali Office)

**TEL +971-4-8870-988**  
FAX +971-4-8870-405

### JFE-TC BEIJING

Unit 1717-1718 Tower B, Gemdale Plaza,  
No. 91, Jianguo Road, Chaoyang District,  
Beijing, China

(c/o M-I Tubulars(Beijing) Co., Limited)

**TEL +86-10-8580-5881**



Cat. No. E1E-015-02

### HOUSTON

10777 Westheimer, Suite 1010  
Houston, TX 77042  
USA

TEL +1 713-986-9000

**JFE-TC**  
technical  
centers  
[jfetc.com](http://jfetc.com)

### SINGAPORE

31 Jurong Port Rd  
05-10 Jurong Logistics Hub  
Singapore 619115

TEL +65-6264-1801

## JFE Steel Corporation

<http://www.jfe-steel.co.jp/en/>

<b>TOKYO HEAD OFFICE</b>	Hibiya Kokusai Building, 2-3 Uchisaiwaicho 2-chome, Chiyodaku, Tokyo 100-0011, Japan Phone: (81)3-3597-3111 Fax: (81)3-3597-4860
<b>NEW YORK OFFICE</b>	JFE Steel America, Inc., New York Office 600 Third Avenue, 12th Floor, New York, NY 10016, U.S.A. Phone: (1)212-310-9320 Fax: (1)212-308-9292
<b>HOUSTON OFFICE</b>	JFE Steel America, Inc., Houston Office 10777 Westheimer, Suite 230, Houston, TX 77042, U.S.A. Phone: (1)713-532-0052 Fax: (1)713-532-0062
<b>BRISBANE OFFICE</b>	JFE Steel Australia Resources Pty Ltd. Level 28, 12 Creek Street, Brisbane, QLD 4000, Australia Phone: (61)7-3229-3855 Fax: (61)7-3229-4377
<b>RIO DE JANEIRO OFFICE</b>	JFE Steel do Brasil LTDA / JFE Steel Corporation, Rio de Janeiro Office Praia de Botafogo, 228 Setor B, Salas 508 & 509, Botafogo, CEP 22250-040, Rio de Janeiro-RJ, Brazil Phone: (55)21-2553-1132 Fax: (55)21-2553-3430
<b>LONDON OFFICE</b>	JFE Steel Europe Limited 15th Floor, The Broadgate Tower, 20 Primrose Street, London EC2A 2EW, U.K. Phone: (44)20-7426-0166 Fax: (44)20-7247-0168
<b>DUBAI OFFICE</b>	JFE Steel Corporation, Dubai Office P.O.Box 261791 LOB19-1208, Jebel Ali Free Zone Dubai, U.A.E. Phone: (971)4-884-1833 Fax: (971)4-884-1472
<b>NEW DELHI OFFICE</b>	JFE Steel India Private Limited 1101, 11th Floor, Unitech's Signature Tower, Tower-A, South City-I, NH-8, Gurgaon, Haryana, 122002, India Phone: (91)124-426-4981 Fax: (91)124-426-4982
<b>MUMBAI OFFICE</b>	JFE Steel India Private Limited Mumbai Office 308, A Wing, 215 Atrium, Andheri - Kurla Road, Andheri (East), Mumbai - 400093, Maharashtra, INDIA Phone: (91)22-3076-2760 Fax: (91)22-3076-2764
<b>SINGAPORE OFFICE</b>	JFE Steel Asia Pte. Ltd. 16 Raffles Quay, No. 15-03, Hong Leong Building, 048581, Singapore Phone: (65)6220-1174 Fax: (65)6224-8357
<b>BANGKOK OFFICE</b>	JFE Steel (Thailand) Ltd. / JFE Steel Corporation, Bangkok Office 22nd Floor, Abdulrahim Place 990, Rama IV Road, Bangkok 10500, Thailand Phone: (66)2-636-1886 Fax: (66)2-636-1891
<b>VIETNAM OFFICE</b>	JFE Steel Corporation, Vietnam Office Unit 1401, 14th Floor, Kumho Asiana Plaza, 39 Le Duan Street, Dist 1, HCMC, Vietnam Phone: (84)8-3825-8576 Fax: (84)8-3825-8562
<b>JAKARTA OFFICE</b>	JFE Steel Corporation, Jakarta Office 6th Floor Summitmas II, JL Jendral Sudirman Kav. 61-62, Jakarta 12190, Indonesia Phone: (62)21-522-6405 Fax: (62)21-522-6408
<b>MANILA OFFICE</b>	JFE Steel Corporation, Manila Office 23rd Floor 6788 Ayala Avenue, Oledan Square, Makati City, Metro Manila, Philippines Phone: (63)2-886-7432 Fax: (63)2-886-7315
<b>SEOUL OFFICE</b>	JFE Steel Korea Corporation 6th Floor, 410, Teheran-ro, Gangnam-gu, Seoul, 135-570, Korea (Geumgang-Tower, Daechi-dong) Phone: (82)2-3468-4130 Fax: (82)2-3468-4137
<b>BEIJING OFFICE</b>	JFE Steel Corporation Beijing 1720 Beijing Fortune Building No.5, Dongsanhuan North Road, Chaoyang District, Beijing, 100004, P.R.China Phone: (86)10-6590-9051 Fax: (86)10-6590-9056
<b>SHANGHAI OFFICE</b>	JFE Consulting (Shanghai) Co., Ltd. Room 801, Building A, Far East International Plaza, 319 Xianxia Road, Shanghai 200051, P.R.China Phone: (86)21-6235-1345 Fax: (86)21-6235-1346
<b>GUANGZHOU OFFICE</b>	JFE Consulting (Guangzhou) Co., Ltd./ JFE Steel Corporation, Guangzhou Office Room 3901, Citic Plaza, 233 Tian He North Road, Guangzhou 510613, P.R.China Phone: (86)20-3891-2467 Fax: (86)20-3891-2469

### Notice

While every effort has been made to ensure the accuracy of the information contained within this publication, the use of the information is at the reader's risk and no warranty is implied or expressed by JFE Steel Corporation with respect to the use of information contained herein. The information in this publication is subject to change or modification without notice. Please contact the JFE Steel office for the latest information.